



3D Neutron Diffraction

Cereser, Alberto; Strobl, M.; Hall, S.; Steuwer, A.; Tremsin, A.; Bergbäck Knudsen, Erik; Willendrup, Peter Kjær; Kabra, S.; Kelleher, J.; Kiyanagi, R.

Total number of authors:

14

Publication date:

2015

Document Version

Publisher's PDF, also known as Version of record

[Link back to DTU Orbit](#)

Citation (APA):

Cereser, A., Strobl, M., Hall, S., Steuwer, A., Tremsin, A., Bergbäck Knudsen, E., Willendrup, P. K., Kabra, S., Kelleher, J., Kiyanagi, R., Kockelmann, W., Peetermans, S., Shinohara, T., & Schmidt, S. (2015). *3D Neutron Diffraction*. Poster session presented at 4th Annual Niels Bohr International Academy Workshop-School on ESS Science, Copenhagen, Denmark.

General rights

Copyright and moral rights for the publications made accessible in the public portal are retained by the authors and/or other copyright owners and it is a condition of accessing publications that users recognise and abide by the legal requirements associated with these rights.

- Users may download and print one copy of any publication from the public portal for the purpose of private study or research.
- You may not further distribute the material or use it for any profit-making activity or commercial gain
- You may freely distribute the URL identifying the publication in the public portal

If you believe that this document breaches copyright please contact us providing details, and we will remove access to the work immediately and investigate your claim.

3D Neutron Diffraction

A Cereser^{1,2}, M Strobl², S Hall^{2,3}, A Steuwer⁴, A Tremsin⁵, EB Knudsen¹,
P Willendrup¹, S Kabra⁶, J Kelleher⁶, R Kiyanagi⁷, W Kockelmann⁶,
S Peetermans⁸, T Shinohara⁷ and S Schmidt¹

¹Technical University of Denmark - ²ESS-AB - ³Lund University - ⁴Business Region Skåne -
⁵University of California at Berkeley – ⁶ISIS – ⁷J-PARC – ⁸PSI

3D Neutron Diffraction (3DND) is a new technique to study shape and orientation of the individual grains composing polycrystalline samples. 3DND enables non-destructive 3D grain mapping of mm- to cm-sized samples, covering larger sample volumes than existing X-ray methods like 3D X-Ray Diffraction (3DXRD) [1]. 3DND would complement 3DXRD, providing information on mechanical evolution, stress/strain states, recrystallization and allowing in-situ studies under extreme conditions.


We are developing the algorithms for the 3D reconstruction based on datasets collected at BL18 (J-PARC), ENGIN-X (ISIS), ICON (PSI), and virtual experiments done using McStas [2].

These are the approaches we used:

1. Laue diffraction, with wide bandwidth and a near-field diffraction detector in backscattering mode.
2. Time-of-flight diffraction, with transmission data collected by a near-field detector and diffraction data collected by far-field ones.

Time-of-flight 3DND


In June 2014 at BL18 we analysed an Armco Iron sample (length: 5 cm, diameter: 1 cm, 99.8% purity), prepared to contain mm-sized grains. The sample was scanned over 180deg in 3deg steps, acquisition time per projection ~1h.



Setup used at BL18. Data were acquired simultaneously by near- (indicated by red arrow) and far-field detectors.


Near- field (NF) detector	MCP detector, 28x28mm ² 1200 fr/s, pixel size 55μm Use: shape of the grains
Far-field (FF) detectors	36 det, each 256x256mm ² Pixel size 4 mm, Q: 0.6-30.7 Use: orientation of the grains

Data collected by near- and far-field detectors at BL18, Fe sample



Data analysis

Data acquired simultaneously by NF and FF detectors



3DND is a nondestructive technique to investigate, in a reasonable time frame, the 3D structure of mm- to cm-sized polycrystalline samples. It completes existing X-ray techniques, enabling to use complex sample environments. Combined with a time-of-flight beam, 3DND can be used to study samples composed by a large number of grains. Once the reconstruction algorithm is fully implemented, we will apply 3DND to study shape memory alloys.

[1] HF Poulsen et al. (2001). [2] K Lefmann and K Nielsen (1999). [3] T Ohhara et al (2009). [4] S Schmidt (2014). [5] W Ludwig et al (2008)



Alberto Cereser - PhD
student at the Technical
University of Denmark.
alcer@fysik.dtu.dk

